

ABSTRACT OF THE DISCLOSURE

There is provided inexpensive maraging steel having high fatigue strength and maraging steel strip formed by use of the same. The maraging steel having high fatigue strength, consisting essentially, by mass, of not more than 0.008% C, from 0 inclusive but not more than 2.0% Si, from 0 inclusive but not more than 3.0% Mn, not more than 0.010% P, not more than 0.005% S, 12 to 22% Ni, 3.0 to 7.0% Mo, less than 7.0% Co, not more than 0.1% Ti, not more than 2.0% Al, less than 0.005% N, not more than 0.003% O (oxygen), and the balance substantially Fe, a total amount of $(3\text{Si} + 1.8\text{Mn} + \text{Co}/3 + \text{Mo} + 2.6\text{Ti} + 4\text{Al})$ being in a range of 8.0 to 13.0%.

09739387-121900